

# KING CUTTINGBOARD®

## Professional High Density Polyethylene Cutting Board

### Tolerances

Gauges

Width/Length

1/4" - 1" ± 5%

Plus Only at Room Temp.

Properties	Units	ASTM	Nominal Values
Density	g/cc	D1505	.96
Tensile Strength @ Yield	psi	D638	>4100
Tensile Modulus	psi	D638	225,000
Elongation @ Break	%	D638	>600
Elongation @ Yield	%	D638	9.8
Flexual Modulus	psi	D790	185,000
Flexual Stress@5% Strain	psi	D790	3,810
Compressive Properties 10% Stain	psi	D695	4,950
Durometer	Shore D	D2240	68
Tensile Impact	ft lbs/in <sup>2</sup>	D1822	115
Izod Impact Resistance	ft lbs/in <sup>2</sup>	D256	1.1
Brittleness Temp.	°F	D746	<-105°
Vicat Softening	°F	D1525	253°
Heat Deflection Temp. 66p.s.i.	°F	D648	167°
Screw and Nail Withdrawl	lbs	D1761	657 & 63
Flamability	Rating	UL94	HB

\*All values are determined on specimens prepared according to ASTM Standards. Nominal values should not be interpreted as specifications.

King CuttingBoard® is made entirely from FDA and USDA approved materials.

King CuttingBoard® meets ASTM D4976 PE235

King CuttingBoard® is NSF approved for Standard 2 & 51

King Plastic Corporation (KPC) makes no representations or warranties and there are no conditions with respect to accuracy, reliability, or application of the information herein, its products or the safety or suitability thereof, or results obtained, whether expressed or implied including, without limitation, any implied warranty of merchantability of fitness for a particular purpose. Buyers and users must determine the results to be obtained from the application of the information herein and the safety and suitability of KPC's products for their own purposes and assume all risk, responsibility, and liability for all injuries, losses, or damages arising from the application of the information herein or use of KPC's products, whether or not occasioned by KPC's negligence or based on strict product liability. KPC neither assumes nor authorizes any person to assume for it any liability in connection with the use of the information herein or its products.



King Plastic Corporation  
1100 N. Toledo Blade Blvd., North Port, FL 34288 USA  
TEL: (941) 493-5502 FAX: (941) 497-3274  
www.kingplastic.com