## CUTTING BOARD®

## **Tolerance information:**

Gauges 1/4" up to 1"  $\pm$  5% Length and width plus only at room temperature

See King CuttingBoard® XL if reduced weight is desired Custom sheet sizes and gauges available

| Properties                        | Units                    | ASTM  | Nominal Values   |
|-----------------------------------|--------------------------|-------|------------------|
| Density                           | g/cc                     | D1505 | 0.955            |
| Tensile Strength @ Yield          | psi                      | D638  | >4,100           |
| Tensile Modulus                   | psi                      | D638  | 255,000          |
| Elongation @ Break                | %                        | D638  | >600             |
| Elongation @ Yield                | %                        | D638  | 9.8              |
| Flexural Modulus                  | psi                      | D790  | 185,000          |
| Flexural Stress @ 5% Strain       | psi                      | D790  | 3,810            |
| Compressive Properties 10% Strain | psi                      | D695  | 4,950            |
| Durometer                         | Shore D                  | D2240 | 68               |
| Tensile Impact                    | ft.lbs./in.²             | D1822 | 115              |
| Izod Impact Resistance            | ft.lbs./in. <sup>2</sup> | D256  | 1.1              |
| Brittleness Temp.                 | °C (°F)                  | D746  | <-76°C (<-105°F) |
| Vicat Softening Temp.             | °C (°F)                  | D1525 | 123°C (253°F)    |
| Heat Deflection Temp. 66 psi      | °C (°F)                  | D648  | 75°C (167°F)     |
| Screw and Nail Withdrawal         | lbs                      | D1761 | 657 & 63         |
| Flammability                      | Rating                   | UL94  | НВ               |
|                                   |                          |       |                  |

All values are determined on specimens prepared according to ASTM standards.

Nominal values should not be interpreted as specifications.

King CuttingBoard® is made entirely from FDA and USDA approved material.

King CuttingBoard® meets ASTM D4976.

King CuttingBoard® is NSF approved for Standards 2 & 51.

The raw material used to make King CuttingBoard® does not contain BPA's or Phthalates.

King Plastic Corporation Limit of Warranty is your money refunded or defective material replaced. All statements, information and data given herein are believed to be accurate and reliable. It is presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patient infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.

