# PIPEGRADE®

# Black PE-4710 High Density Polyethylene

### **Tolerance information:**

### K-Stran™

Gauges 1/8" through 1-1/2" ± 5% | Length and width plus only at room temperature

## **Compression Molding**

Gauges greater than 1" and under 1-1/2"  $\pm$  10% | Gauges 1-1/2" and greater plus only | Length and width plus only at room temperature

Custom thickness up to 25"/635mm with our King Size Blocks and Massive Shapes Custom Sizes Available up to 96" width and 100'+ in length

Properties	Units	ASTM	Nominal Values
Density	g/cc	D792	0.949
Tensile Strength @ Break	psi	D638	5,510
Tensile Strength @ Yield	psi	D638	3,630
Elongation @ Break	%	D638	600
Flexural Modulus 2% secant	psi	D790	150,000
Notched Izod Impact	ft.lbs./in.²	D256	9.2
Brittleness Temp.	°C (°F)	D746	-118°C (-180°F)
Vicat Softening Temp.	°C (°F)	D1525	126°C (259°F)
Environmental Stress Crack Resistance	hrs	D1693C	>5,000
Notch Tensile (PENT)	hrs	F1473	>10,000

All values are determined on specimens prepared according to ASTM Standards.

Nominal values should not be interpreted as specifications.

Listed by the Plastic Pipe Institute as a PE4710 material with Hydrostatic Design Basis of 1600 psi @ 73°F and 1000 psi @ 140°F.

King PipeGrade® meets ASTM D3350 cell class 445574C.

King PipeGrade® is made with materials that comply with NSF/ANSI Standard 14 to be used in potable water piping systems.

King Plastic Corporation Limit of Warranty is your money refunded or defective material replaced. All statements, information and data given herein are believed to be accurate and reliable. It is presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patient infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.

