

KING STARBOARD®

Tolerance information:

Tolerance information: Gauges 1/4" up to 1-1/2" ± 5%
Length and width plus only at room temperature

Custom sheet sizes, gauges, and colors available upon request

Properties	Units	ASTM	Nominal Values
Density	g/cc	D1505	0.963
Tensile Strength @ Yield	psi	D638	>4,500
Tensile Modulus	psi	D638	318,000
Elongation @ Break	%	D638	>600
Elongation @ Yield	%	D638	8.8
Flexural Modulus	psi	D790	225,000
Flexural Stress @ 5% Strain	psi	D790	4,480
Compressive Properties 10% Strain	psi	D695	4,790
Durometer	Shore D	D2240	69
Tensile Impact	ft.lbs./in. ²	D1822	99
Izod Impact Resistance	ft.lbs./in. ²	D256	1.4
Brittleness Temp.	°C (°F)	D746	<-75°C (<-103°F)
Vicat Softening Temp.	°C (°F)	D1525	132°C (270°F)
Heat Deflection Temp. 66 psi	°C (°F)	D648	84°C (183°F)
Screw and Nail Withdrawal	lbs	D1761	755 & 55
Flammability	Rating	UL94	HB

All values are determined on specimens prepared according to ASTM standards.

Nominal values should not be interpreted as specifications.

King StarBoard® ST is made entirely from FDA and USDA approved material.

King StarBoard® ST meets ASTM D4976.

King StarBoard® ST contains no VOC's.

King Plastic Corporation Limit of Warranty is your money refunded or defective material replaced. All statements, information and data given herein are believed to be accurate and reliable. It is presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.



King Plastic Corporation
Our Innovation. Your Imagination.®

1100 N. Toledo Blade Blvd. | North Port, FL 34288 USA
P: 941.493.5502 | F: 941.497.3274 | www.kingplastic.com