



Tolerance information:

K-Stran™

Gauges 1/16" through 1-1/2" ± 5% | Length and width plus only at room temperature

Compression Molding

Gauges greater than 1" and under 1-1/2" ± 10% | Gauges 1-1/2" and greater plus only | Length and width plus only at room temperature

Custom thickness up to 25"/635mm with our King Size Blocks and Massive Shapes

Custom sheet sizes, gauges and colors available

Properties	Units	ASTM	Nominal Values
Density	g/cc	D1505	0.918
Tensile Strength @ Yield	p.s.i.	D638	>1,400
Elongation @ Break	%	D638	>500
Flexural Modulus	p.s.i.	D790	30,000
Durometer	Shore D	D785	42
Notched Izod Impact	ft. lbs/in. ²	D256	No Break
Vicat Softening Temp.	°C (°F)	D1525	89°C (192°F)
Brittleness Temp.	°C (°F)	D746	<-76°C (<-105°F)
Heat Deflection Temp. 66p.s.i.	°C (°F)	D648	50°C (122°F)
Haze	%	D1003	12.7
Dart Drop Impact Strength	g	D1709	130
Elmendorf Tear Strength	g	D1922	340

King KPC LDPE meets FDA 21 CFR 177.1520.

King KPC LDPE meets the requirements of Mil-P-23536 Rev A.

King KPC LDPE meets the requirements of EU Food Contract.

King KPC LDPE meets ASTM D4976.

King KPC LDPE is RoHS compliant.

King Plastic Corporation Limit of Warranty is your money refunded or defective material replaced. All statements, information and data given herein are believed to be accurate and reliable. It is presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.

