

KING PLASTI-SHIELD®

5% Borated

Tolerance information:

K-Stran™

Gauge 1" ± 5%

Length and width plus only at room temperature

Compression Molding

Gauge 1" ± 10%

Custom sheets, blocks and slabs available in standard or custom colors

Properties	Units	ASTM	Nominal Values
Density (5% Borated)	g/cc	D1505	0.98
Tensile Strength @ Yield	p.s.i.	D638	3,960
Durometer	Shore D	D2240	66
Vicat Softening	°C (°F)	D1525	89°C (192°F)

All values are determined on specimens prepared according to ASTM Standards.

Thickness required to attenuate a neutron beam by a factor of 10. M.

King Plastic Corporation Limit of Warranty is your money refunded or defective material replaced. All statements, information and data given herein are believed to be accurate and reliable. It is presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.



King Plastic Corporation
Our Innovation. Your Imagination.®

1100 N. Toledo Blade Blvd. | North Port, FL 34288 USA
P: 941.493.5502 | F: 941.497.3274 | www.kingplastic.com