



Healthcare Products



The Antimicrobial Polymer Building Sheet for Healthcare Applications

King MediGrade® is a super tough polymer building sheet with an advanced antimicrobial technology for protecting the product surface against stain and odor causing bacteria, algae and fungi. The antimicrobial agent is bonded at the molecular level and will not leach out of the product. Unlike surface antimicrobials, the advanced antimicrobial technology protects against bacterial degradation for the lifetime of the product. Healthcare facilities, medical equipment and case goods made with King MediGrade® will stay cleaner and fresher between cleanings. Studies have shown that surfaces with the antimicrobial technology can inhibit the amount of certain product-damaging bacteria by 99.9999%* compared to an untreated surface.

KING
MEDIGRADE®

Applications

- Cabinetry and Storage Carts
- Clean Rooms
- Dental Facilities
- Hospitals
- Locker Rooms
- Medical Facilities
- Medical Laboratories
- Mobile Computer Carts
- Nursing Homes
- Nurses Stations
- Rest Rooms
- Veterinary Facilities

Specifications

Standard Sheet Size

in: 48" x 96"

mm: 1219mm x 2438mm

Standard Gauges

in: 1/4" | 1/2" | 3/4"

mm: 6.4mm | 12.7mm | 19mm

Approximate Weight

lbs: 40 lbs | 80 lbs | 120 lbs

kg: 18kg | 36kg | 54.4kg

Tolerance information:

Gauges 1/4" up to 3/4" ± 5%

Length and width plus only at room temperature

Custom sheet sizes, gauges, and colors available upon request


Standard Colors



Dolphin Gray



Sansshade



Seafoam



White/White

Note: Color accuracy can vary considerably on computer monitors and printers. Please consult your distributor for a product sample before making critical color choices.

Disclaimer: The antimicrobial may affect color.

*For bacteriostatic, fungistatic, & algistatic properties. This product is exempt from registration under 40 CFR 152.25(a). King MediGrade® effectiveness verified by ISO and ASTM standards. This product does not protect users or others from disease-causing bacteria. Always clean this product thoroughly after use.

Properties	Units	ASTM	Nominal Values
Density	g/cc	D1505	0.96
Tensile Strength @ Yield	psi	D638	>4,500
Tensile Modulus	psi	D638	318,000
Elongation @ Break	%	D638	>600
Elongation @ Yield	%	D638	8.8
Flexural Modulus	psi	D790	225,000
Flexural Stress @ 5% Strain	psi	D790	4,480
Compressive Properties 10% Strain	psi	D695	4,790
Durometer	Shore D	D2240	69
Tensile Impact	ft.lbs./in. ²	D1822	99
Izod Impact Resistance	ft.lbs./in. ²	D256	1.4
Brittleness Temp.	°C (°F)	D746	<-75°C (<-103°F)
Vicat Softening Temp.	°C (°F)	D1525	172°C (270°F)
Heat Deflection Temp. 66 psi	°C (°F)	D648	84°C (183°F)
Screw and Nail Withdrawal	lbs	D1761	755 & 55
Flammability	Rating	UL94	HB

All values are determined on specimens prepared according to ASTM.

Nominal values should not be interpreted as specifications.

King MediGrade® is made entirely from FDA and made with USDA approved materials. King MediGrade® meets ASTM D4976.

King MediGrade® contains no VOC's.



King Plastic Corporation
Our Innovation. Your Imagination.®

1100 N. Toledo Blade Blvd. | North Port, FL 34288 USA
P: 941.493.5502 | F: 941.497.3274 | www.kingplastic.com